

Natural Wood Oil

Water-based oil. Invisible look on wood.

Natural Wood Oil is a water-based oil for wood floors with invisible look. It gives the wood a natural, clear and extremely opaque appearance, with a pleasant sensation of softness to the touch - soft touch effect. It also guarantees high performance of resistance to scratches, wear and stains, which can be further increased by adding the hardener B Plus to the product. Natural Wood Oil is partially formulated with bio-renewable resins of vegetable origin. Natural Wood Oil is safe, with a low VOC and is certified according to EN 71-3.

Technical data at 20 °C and 60% r.h.

Aspect	White liquid
Density	1,022 kg/litre
pH	7,5
Dust dry	1 hour
Light traffic	3 – 4 hours (with care)
Sanding	4 – 5 hours
Ready for traffic	Minimum 24 hours
Yield	12 – 14 m ² /litre
Resistance to abrasion after 7 days	25 mg – Taber Abraser, wheels CS10, 1000 g, 1000 revolutions
Gloss degree (60°)	< 5 gloss
Application temperature	> 10 °C – Frost sensitive
VOC	45 g/litre, cat A/i (WB) limit 140 g/litre (2004/42/CE)
Storage	12 months in original sealed package at temperature > 10 °C
Tools cleaning	Clean the roller immediately after use with water and neutral soap with the help of a 'roller wringer' until the roller itself is no longer soaked in opalescent liquid; if possible rinse again with clean water. Store the rollers in Soluzione di Lavaggio S/28 suitably diluted; rinse with clean water before using them again.
Packaging available	Metal cans of 1 o 2.5 litres

Application

Sand the wooden floor as usual, eliminating any residue from the previous treatment. If necessary, fill the cracks with one of the Tover fillers: Idrostucco RS/30, water based (preferable), Lega Stucco RS/A or Lega Stucco RS/20, solvent based. Remove the grout residues with 100 or 120 grit sandpaper. Vacuum the dust and clean the surface thoroughly. Mix the product in its packaging, pour it into a suitable container and apply evenly with a roller or brush. After 4 – 5 hours, sand with a 180 – 220 fine-grained mesh and apply a second coat. For high traffic or stained surfaces, it is possible to complete the finish with a third coat after 3 – 4 hours, without sanding. Always check that the environmental conditions are suitable for finishing. In the presence of large surfaces and high ambient temperatures or low humidity, it is recommended to add 5% of retardant additive Rallenty to the product.

To further increase its chemical and mechanical resistance characteristics, add 10% of hardener B Plus or Eco B Plus to Natural Wood Oil. After mixing, the product can be used for about 4 hours.



Varnishes & Finishing

Natural Wood Oil



Certifications



TOVER[®]
Your formula

MADE IN ITALY

Tover S.r.l.
Via Rosa Luxemburg, 2/A - Collegno (TO) - ITALY
P. IVA 07783540011 - REA n. 920259
Tel. +39/011.7792823 - Fax. +39/011.7792749
www.tover.com - info@tover.com

Notes

Frost sensitive

Do not use on solvent based primers

Do not use the product outdoor

Do not pour the product directly on the floor.

Avoid treating the perimeter and the whole of the room in two stages. Proceed for small perimeter sections and immediately pass to the adjacent area.

During application, avoid direct sunlight on the floor

Avoid drafts

Switch off heating system especially if underfloor

Maintenance

For the frequent cleaning and maintenance of the floors treated with this product we recommend the use of the neutral Deteroil soap or sanitizer Saniparquet, for extraordinary maintenance, we suggest Lux Matt liquid wax.

Safety rules

Product for professional use. Strictly comply with what is stated on the labelling and consult the safety data sheet before using the product.

Disposing of waste

Dispose of the unused product and empty packaging in accordance with the provisions of the local legislation in force.



Varnishes &
Finishing

Natural Wood Oil



Certifications



The information contained in this technical data sheet are for guidance only and they do not hold our responsibility. Adapt the use of our products to the environmental conditions and materials to be treated.

Rev 01 – 24/09/2020. Current Technical Data Sheet replaces the previous one.